














Substrate		DIN 60001	100 % polyester
Weave		DIN ISO 9354	woven fabric
Weight approx.		DIN EN ISO 2286-2	315 g/m <sup>2</sup> (without liner) 410 g/m <sup>2</sup> (with liner)
Fire retardancy			no
Application			indoor
Width		DIN EN ISO 2286-1	100 cm / 39 inch
Print side			outside
Roll length			30 ± 0,5 m
Care instruction		DIN EN 12956	scrub resistant (grade 5) according to instruction*
Type of ink		 SOL VENT  UV  LATEX	all kinds of solvent inks, UV-curable inks, latex inks

## Advantages

- reverse film easy to remove
- easy to clean
- opaque
- trimming cold (no fraying)
- easy handling, print & cut
- able to plott

## Applications

- blackout
- wall covering\*\*

\* please have a look at the cleaning instructions on [www.jm-mediatex.com](http://www.jm-mediatex.com)

\*\* please test in advance; the adhesive behavior depends on the surface applied;  
please have a look at the processing instructions on [www.jm-mediatex.com](http://www.jm-mediatex.com)



All details are nominal values and are subject to change within usual tolerances (± 5 %). The information provided in this document is based on current knowledge and experience. They do not exempt a manufacturer/processor from carrying out their own tests and trials as their in-house handling and manufacturing processes can have a significant range of influences on outcomes. Application, utilisation and processing of products is taking place outside of our control and are therefore the sole responsibility of the manufacturer/processor. date: 01/2020