

# Interlam™

## EcoTex™

Interlam™ EcoTex™ is a 4.7 mil (120µ) PP laminating film with a pebble textured finish, coated on one side with a pressure sensitive, aqueous acrylic adhesive that is protected by a bleached Kraft release paper coated on one side with siliconised PE. Interlam™ EcoTex™ is phthalate-free and provides excellent image enhancement for indoor graphics. It holds several slip ratings and certifications making it ideal for public spaces.

- THE SCUFF-RESISTANT, PEBBLE TEXTURED FINISH MAKES THIS LAMINATING FILM SUITABLE FOR GRAPHICS WHERE EXTENSIVE HANDLING MAY BE INVOLVED
- IDEAL FOR LAMINATING AND ENCAPSULATING TRADESHOW AND BANNER STAND GRAPHICS, SIGNAGE IN HIGH TRAFFIC AREAS, COUNTER MATS, PLACEMATS, AND OTHER GRAPHICS WHERE A SCUFF-RESISTANT FINISH IS REQUIRED AND COST IS A KEY FACTOR
- IDEAL FOR SINGLE-SIDED LAMINATION DUE TO ITS DIMENSIONAL STABILITY
- OFFERS EXCELLENT UV PROTECTION FOR HIGH QUALITY IMAGES, PHOTOGRAPHIC PRINTS, WALLCOVERINGS, AND SELF-ADHESIVE VINYL

For more information, performance and warranty guide lines please contact your local Drytac office.

© 2020 Drytac Corporation. E&OE.  
All other trademarks are the property of their respective owners.

## TECHNICAL SPECIFICATION

### PRODUCT STRUCTURE

<b>Film</b>	Pebble Textured PP
<b>Adhesive</b>	Aqueous Acrylic (Pressure Sensitive)
<b>Release Liner</b>	Siliconised 1 Side PE Coated Kraft

### PRODUCT CHARACTERISTICS

<b>Film Thickness</b>	4.7 mil (120µ)   5.7 mil (145µ)
<b>Adhesive Layer</b>	1 mil (25µ)
<b>UV Protection</b>	Yes
<b>Outdoor Durability</b>	Not Applicable
<b>Service Temperature Range</b>	-4°F to 248°F (-20°C to 120°C)
<b>Peel Strength (20 min, FTM1)</b>	11 N/25mm
<b>Slip Ratings</b>	<ul style="list-style-type: none"><li>● EN 13036-4/ASTM E303: Low Slip Potential; Dry: 71 Moderate Slip Potential; Wet: 25</li><li>● R10 (DIN 51130:2010)</li></ul>
<b>Shelf Life</b>	2 Years
<b>Storage Conditions</b>	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity

### PROCESS SETTINGS

Equipment Type & Temperature	Speed
<b>Roller Laminator</b> Room temperature to 104°F (40°C)	1 ft to 8 ft (0.3m to 2.5m) per minute
<b>Press</b>	Not recommended

**DRYTAC®**  
ADHESIVE SCIENCE

#### Europe

Filwood Road,  
Fishponds,  
Bristol, BS16 3RY,  
United Kingdom  
bristol@drytac.com  
Tel: +44 (0) 117 958 6500

#### Canada

30 Driver Road,  
Brampton,  
Ontario, L6T 5V2,  
Canada  
toronto@drytac.com  
Tel: +1 800.353.2883

#### USA

5401-B Eubank Road,  
Sandston,  
Virginia, 23150,  
USA  
customerservice@drytac.com  
Tel: +1 800.280.6013