

# Technical data sheet

## Prime Protection Paper

| PRODUCT NAME        |  | PRIME PROTECTION PAPER |  |
|---------------------|--|------------------------|--|
| ISO STANDARD        |  |                        |  |
| Grammage            |  | SS-EN ISO 536          |  |
| Air resistance      |  | 5636-5                 |  |
| Tensile strength MD |  | ISO 18522              |  |
| Tensile strength CD |  | ISO 18522              |  |
| Elongation MD       |  | ISO 18522              |  |
| Elongation CD       |  | ISO 18522              |  |
| Tear strength MD    |  | ISO 18522              |  |
| Tear strength CD    |  | ISO 18522              |  |
| Moisture            |  | SS-EN 20287            |  |
| NORMVALUE           |  |                        |  |
| Grammage            |  | 19 g/m2                |  |
| Air resistance      |  | 115 s                  |  |
| Tensile strength MD |  | 2.20 Kn/m              |  |
| Tensile strength CD |  | 1.00 Kn/m              |  |
| Elongation MD       |  | 2.20 %                 |  |
| Elongation CD       |  | 1.70 %                 |  |
| Tear strength MD    |  | 160 mN                 |  |
| Tear strength CD    |  | 210 mN                 |  |
| Moisture            |  | 6.5 %                  |  |