

Technical data sheet

Prime Protection Paper

PRODUCT NAME		PRIME PROTECTION PAPER	
ISO STANDARD			
Grammage		SS-EN ISO 536	
Air resistance		5636-5	
Tensile strength MD		ISO 18522	
Tensile strength CD		ISO 18522	
Elongation MD		ISO 18522	
Elongation CD		ISO 18522	
Tear strength MD		ISO 18522	
Tear strength CD		ISO 18522	
Moisture		SS-EN 20287	
NORMVALUE			
Grammage		25 g/m2	
Air resistance		115 s	
Tensile strength MD		2.20 Kn/m	
Tensile strength CD		1.00 Kn/m	
Elongation MD		2.20 %	
Elongation CD		1.70 %	
Tear strength MD		160 mN	
Tear strength CD		210 mN	
Moisture		6.5 %	